

Harzverbräuche



Artikelbezeichnung	Anwendung	Dicken in mm	Harzverbrauch g/m ² /mm	Beispiele:				
				Dicke in mm	Fasergewicht g/m ²	Harzverbrauch g/m ²	Gesamtgewicht g/m ²	Dichte g/cm ³
sphere.core S	hand layup	5,0 - 1,0	600 - 650	2,0	70	1.200	1.270	0,64
sphere.core SP	hand layup	5,0 - 1,0	600 - 650	2,0	80	1.250	1.330	0,67
sphere.core SBC	hand layup	10,0 + 8,0 + 6,0	380 - 420	8,0	270	3.200	3.470	0,43
Guncore	spray up		650	5,0	500	3.250	3.750	0,75
sphere.tex	hand layup	3,0 + 2,0 + 1,5	500 - 550	2,0	170	1.050	1.220	0,61
sphere.ax S	hand layup	4,0 + 3,0 + 2,0	500 - 550	3,0	300	1.600	1.900	0,63
sphere.ax IP	RTM-light	5,0 - 3,0	500,0	4,0	480	2.000	2.480	0,62
sphere.ax IP	VIP 0,6	5,0 - 3,0	400-450	2,5	480	1.050	1.530	0,61
sphere.core SBC IP	RTM-light	10,0 + 8,0 + 6,0	400-450	8,5	540	3.600	4.140	0,49
sphere.core SBC IP	VIP 0,6	10,0 + 8,0 + 6,0	380-430	8,0	540	3.400	3.940	0,49